



SANHO CHEMICAL CO., LTD.

NO. 1 CHUNG SHAN S. RD., LU-CHU, KAOSHIUNG, TAIWAN.
TEL : 886-7-6962211~3 [http : // www.sanho.com.tw](http://www.sanho.com.tw)
FAX : 886-7-6976993 (Sales) E-mail : sanho@sanho.com.tw
FAX : 886-7-6961782 (Export) E-mail : sanho@so-net.net.tw

KINGMIDE 305

KINGMIDE 305 is a typical polyaminoamide type epoxy curing agent. KINGMID 305 has large molecular weight, it thus provide the cured products with an epoxy resin with high orders of flexibility and adhesive.

1.SPECIFICATIONS

Appearance	: Brown-colored viscous liquid.
Viscosity (40°C)	: 50,000~70,000 mPa·s
Colour (Gardner)	: 10 Max.
Amine Value	: 240 ±15
A.H.E.W.	: 180
Sp.Gr. (25°C)	: 0.97

2.RECOMMENDED MIXING RATIO

- (1) 30~40 parts by weight to 100 parts of bisphenol-A type epoxy resin whose epoxy equivalent weight is about 450~500.
- (2) 80~120 parts by weight to 100 parts of bisphenol-A type epoxy resin whose epoxy equivalent weight is about 180~200.

3.CURING CHARACTERISTICS

Epoxy Resin : employed bisphenol-A type epoxy resin whose epoxy equivalent weight is about 190.

Total mass : 200gram (23°C)

Mixing Ratio	Epoxy / KINGMIDE 305 = 50 / 50
Peak exothermic time, min.	180
Peak exothermic temperature (°C)	30

4.PHYSICAL PROPERTIES

Epoxy Resin : employed bisphenol-A type epoxy resin whose epoxy equivalent weight is about 190.

Mixing Ratio : Epoxy Resin / KINGMIDE 305 = 50 / 50

Curing condition	80°C×1 hour	80°C×2 hours	23°C×14days
Compressive strength kgf/mm ²	6.0	6.1	
Bending strength kgf/mm ²	7.2	7.1	6.2
Flexural modulus kgf/mm ²	2.9×10 ²	3.1×10 ²	2.1×10 ²



SANHO CHEMICAL CO., LTD.

NO. 1 CHUNG SHAN S. RD., LU-CHU, KAOSHIUNG, TAIWAN.
 TEL : 886-7-6962211~3 [http : // www.sanho.com.tw](http://www.sanho.com.tw)
 FAX : 886-7-6976993 (Sales) E-mail : sanho@sanho.com.tw
 FAX : 886-7-6961782 (Export) E-mail : sanho@so-net.net.tw

5.DRYING PROPERTIES OF CURED FILMS

Epoxy Resin : employ bisphenol-A type epoxy resin whose epoxy equivalent weight is about 190.

Mixture resins of KINGMIDE 305 and epoxy resin, based on following Mixing ratio, were coated onto the mild steel plates with sand blast treatment.

A= Epoxy resin was dissolved with Xylene. (Epoxy resin : Xylene = 70 : 30)

B= Solvents (Xylene : Isobutanol = 80 : 20)

Mixing Ratio A / KINGMIDE 305 / B	100 / 25 / 20	100 / 20 / 15
Drying properties (by Drying recorder, Dry film = 100 μ , 22~23 $^{\circ}$ C)		
Set to touch (hour)	0.65	1.1
Tack free (hour)	10.0	10.5
Dry through (hour)	24	24
Physical properties (Dry film = 100 μ , two time coating, 23 $^{\circ}$ C \times 7days)		
Cross cut	25 / 25	25 / 25
Bending test (2 mm)	OK	OK
Du Pont Impact resistance test (1/2" \times 500gram \times 50cm)	OK	OK
Pencil Hardness	F	2B

6.CHEMICAL PROPERTIES OF CURED FILMS

Epoxy Resin : employ bisphenol-A type epoxy resin whose epoxy equivalent weight is about 190.

A= Epoxy resin was dissolved with Xylene (Epoxy resin : Xylene = 70 : 30)

B= Solvents (Xylene : Isobutanol = 80 : 20)

Weight increase was measured after following chemical substances were permeated into cured products of KINGMIDE 305 with epoxy resin.

Mixing Ratio :		100 / 25 / 20				100 / 20 / 15			
A / KINGMIDE 305 / B		7	14	30	60	7	14	30	60
Immersing days		7	14	30	60	7	14	30	60
5% Acetic acid solution		OK	6M	1L	---	OK	OK	2L	---
5% Sulfuric acid solution		OK	OK	OK	OK	OK	OK	OK	OK
5% Hydrochloric acid solution		OK	OK	OK	OK	OK	OK	OK	9S
10% Ammonia solution		OK	OK	OK	8VS	OK	OK	6VS	4S
10% Caustic soda solution		OK	OK	OK	OK	OK	OK	OK	OK
5% salt solution		OK	OK	OK	9VS	OK	OK	OK	OK
Tap water		OK	OK	OK	9VS	OK	OK	OK	9VS
Kerosene		OK	OK	OK	---	OK	OK	OK	---
Isopropanol		OK	OK	OK	---	OK	OK	OK	---
MIBK		OK	OK	OK	---	OK	OK	OK	---
Salt spray resistance after 70 hours	Cross cut	25 / 25				25 / 25			
	Swelling width	1 mm				2 mm			
	Scribed	Unaffected				Unaffected			

Dry film thickness : 100 (two times coatings)

Curing time : 7 days , at 23 $^{\circ}$ C



SANHO CHEMICAL CO., LTD.

NO. 1 CHUNG SHAN S. RD., LU-CHU, KAOSHIUNG, TAIWAN.

TEL : 886-7-6962211~3

[http : // www.sanho.com.tw](http://www.sanho.com.tw)

FAX : 886-7-6976993 (Sales)

E-mail : sanho@sanho.com.tw

FAX : 886-7-6961782 (Export)

E-mail : sanho@so-net.net.tw

7.SUGGESTED FORMULATIONS

(1) Varnish Formulation :

<u>component 1 :</u>		<u>component 2 :</u>	
Epoxy Resin(EEW :450~575)	400	KINGMIDE 305	200
MIBK	200	Xylene	200
Xylene	400	n-Butanol	100
<hr/>		<hr/>	
Sum of comp.1	1,000	Sum of comp.2	500

(2) Zinc-Rich Primers Formulation :

<u>component 1 :</u> (ball mill base)		<u>component 2 :</u>	
Epoxy Resin(EEW :450~575)	44	KINGMIDE 305	22
Xylene	66	Xylene	12
n-Butanol	36	n-Butanol	9
MIBK	8	<hr/>	
Zinc Dust	900	Sum of comp.2	43
Benton 34	10		
<hr/>			
Sum of comp.1	1,058		

(3) Tar-Epoxy Coating Formulation :

<u>component 1 :</u>		<u>component 2 :</u>	
Epoxy Resin(EEW :450~575)	100	KINGMIDE 305	50
Coal Tar	120	Xylene	25
Pigment / Filler	80	n-Butanol	5
Xylene	180	<hr/>	
MIBK	90	Sum of comp.2	80
Methanol	40		
<hr/>			
Sum of comp.1	610		

(4) Chemical Resistant Formulation :

<u>component 1 :</u>		<u>component 2 :</u>	
Epoxy Resin(EEW :450~575)	122	KINGMIDE 305	65
Strontium chromate	107	Xylene	28
Titanium Dioxide	20	Isopropanol	72
Magnesium Silicate	49	n-Butanol	63
Diatomaceous Silica	26	Cellosolve Solvent	129
MIBK	18	<hr/>	
Xylene	56	Sum of comp.2	357
MEK	102		
<hr/>			
Sum of comp.1	535		