TEL: 886-7-6962211~3 http://www.sanho.com.tw FAX: 886-7-6976993 (Sales) E-mail: sanho@sanho.com.tw FAX: 886-7-6961782 (Export) E-mail: sanho@so-net.net.tw

KINGMIDE 305-70

KINGMIDE 307-60 curing agent is a standard reactive polyamide intended for use in curing of epoxy resin . KINGMIDE 305-70 is cut to 70 % solids by weight in xylene / isobutanol . Whem cured with ac high molecule weight of epoxy resin .it is provides cured films with such high orders desired at actual application field as good flexibility, simultaneously with good

KINGMIDE 305-70 is thus desired for heavy duty primer coatings application of anti corrosion resistance.

1. SPECIFICATIONS

Appearance : Yellow brown viscous liquid.

Non Volatile Matter $: 70 \pm 2\%$ Viscosity (25°C) $: W \sim Z$ Colour : 9 Max.

Amine Value : 170 ± 10 (JIS)

Solents \therefore Xylene \therefore Isobutanol = $7 \div 3$ (by weight)

2. RECOMMENDED MIXING RATIO

water resistance and good alkali resistance.

40~60 parts by weight to 100 parts of epoxy resin whose epoxy equivalent weight is about 490.